

Typical Natural Gypsum Analysis 0-40 mm

	RANGE*	TYPICAL*	MIN*	MAX*
		%	%	%
Ca SO4 2H2O (Calcium Sulphite Dihydrate)	88-95	91	88	95
Free Water	0.0-2.0	1	-	2
Carbonates	0.0-5.0	3	-	5
Ca SO4 (Anhydrite)	0-5.0	3	-	5
Cl	0.00-0.01	0	-	0.01
SiO2 + Insolubles	1.0-3.0	2	-	3
Combined Water	18.00-19.50	18.5	18.50	19.50
SO3	40-45	43	40	-
Dihydrate + Anhydrite	88.00-95.00	93	88	-

Partival Size (by weight)		Estándar Size for Natural gypsum: 0-40 mm
		Fine < 5 mm: max 40%

The typical specifications analysis of the Natural Gypsum is indicative for the BUYER'S information. SELLER and BUYER acknowledge that any variations of the Natural Gypsum to the typical analysis shown above shall not be treated as defects.