

## Typical Natural Limestone Analysis

	TYPICAL	MIN*	MAX*
	%	%	%
<b>SiO<sub>2</sub></b>	1,31		
<b>Al<sub>2</sub>O<sub>3</sub></b>	0,39		
<b>Fe<sub>2</sub>O<sub>3</sub></b>	0,29		
<b>CaO (PPM)</b>	52,89	50	
<b>Choride</b>	200		
<b>MgO</b>	0,66		
<b>K<sub>2</sub>O</b>	0,01		
<b>Caco<sub>3</sub></b>	90	85	
<b>LOI</b>	43,58		
<b>Moisture</b>	3	1	9
<b>Partival Size (by weight)</b>	Standard Size for Natural Limestone: 0-40 mm		
	Fine < 5 mm:		max 25%

*The typical specifications analysis of the Limestone is indicative for the BUYER'S information. SELLER and BUYER acknowledge that any variations of the Natural Limestone to the typical analysis shown above shall not be treated as defects.*