

Typical Natural Gypsum Analysis 0 - 70 mm

	RANGE*	TYPICAL*	MIN*	MAX*
		%	%	%
Ca SO4 2H2O (Calcium Sulphite Dihydrate)	88-95	91	88	95
Free Water	0.0-2.0	1	-	2
Carbonates	0.0-5.0	3	-	5
Ca SO4 (Anhydrite)	0-5.0	3	-	5
Cl	0.00-0.01	0	-	0.01
SiO2 + Insolubles	1.0-3.0	2	-	3
Combined Water	31-33	32	31	33
SO3	18.00-19.50	18.5	18.50	19.50
Dihydrate + Anhydrite	40-45	43	40	-

Partival Size (by weight)		Estándar Size for Natural gypsum: 0-70 mm
		Fine < 5 mm: max 25%

The typical specifications analysis of the Natural Gypsum is indicative for the BUYER'S information. SELLER and BUYER acknowledge that any variations of the Natural Gypsum to the typical analysis shown above shall not be treated as defects.